

About

The BioClean-D Coverall with Hood and Integrated Boots is a disposable garment offering comfort and head-to-toe protection. Featuring a front zip with protective flap, elasticated hood, back, cuffs and ankles, and thumb loops to ensure a secure hold. The integrated boots feature slip-resistant soles to ensure every step is taken with confidence.

Specifications

MATERIAL:

Antistatic BioClean-D CleanTough white material & polyurethane soles

COLOUR:

White

CONSTRUCTION:

Bound seams with single needle stitching

CLASSIFICATION:

PPE Cat 3 Type 5 & 6

CHARACTERISTICS:

Antistatic to EN 1149-5* & low particulating

COMPATIBILITY:

ISO Class 4



HEAD-TO-TOE
PROTECTION

EXCELLENT ESD
PROPERTIES

PPE CAT 3 TYPE 5 & 6

SILICONE-FREE

Specific Applications

- Medical Cell Centers to aid safe handling of culture plates
- Surgical Rooms to aid safe transporting specimens
- GTP level environments to aid safe handling of culture plates

EN 13982 1:2004
+ A1:2010



TYPE 5

EN 13034:2005
+ A1:2009



TYPE 6

EN 1149 5:
2008



Quality Standards

- Manufactured in a facility holding ISO 9001:2015 and (EU)2016/425 Module D certifications
- Conforms to Category 3 - Personal Protective Equipment PPE Regulation (EU)2016/425
- Tested against standard EN ISO 13982-1:2004+A1:2010 protective clothing for use against solid particles (Type 5)
- Tested against standard EN ISO 13034:2005+A1:2009 protective clothing against liquid chemicals (Type 6)
- Tested against standard EN ISO 14325 protective clothing against chemicals
- Tested against permeation standard ASTM F739-12
- Tested against standards: EN 1149-5:2008*, protective clothing - electrostatic properties; EN 530, Abrasion resistance; EN 7854, Flex cracking resistance; EN 6530, Resistance to penetration by liquids; EN 13934-1, Tensile strength; EN 9073-4, Trapezoidal tear resistance; EN 863, Puncture resistance; and EN 13935-2, Seam strength
- Processed in an NEBB certified ISO Class 4 environment

Shelf Life & Storage

Five (5) years from date of manufacture. Store in a dry, cool place (<40°C) away from direct sunlight and fluorescent light.

Performance Test Results – BioClean-D CleanTough White Material

TEST	RESULT		PERFORMANCE CLASS (EN 14325)
Abrasion Resistance	10 to 100 cycles		1
Flex Cracking Resistance	5,000 15,000 cycles		3
Trapezoidal Tear Resistance	CD 29.3 N		2
Trapezoidal Tear Resistance	MD 55.5 N		3
Tensile Strength	MD 97 N		2
Tensile Strength	CD 48 N		1
Puncture Resistance	8 N		1
Repellence to Liquids	30% H ₂ SO ₄	96.3%	3
	10% NaOH	97.6%	3
	O-Xylene	95.7%	2
	Butan-1-ol	96.6%	3
Penetration by Liquids	30% H ₂ SO ₄	0%	3
	10% NaOH	0%	3
	O-Xylene	0%	3
	Butan-1-ol	0%	3
Inward leakage of aerosols of fine particles ¹	Pass		N/A
Resistance to penetration by spray (Spray Test) ¹	Pass		N/A
Seam Strength ²	70 N		2
Electrostatic Charge Half Decay Time, t ₅₀ (secs)	0.07		PASS

¹All interfaces with additional PPE were taped during testing, as required by the standards.

²Seam not destroyed.

Particle Shedding Test Results

TEST	RESULT	CATEGORY (IEST-RP-CC003.3)
Particle Shedding (Helmke Drum Test)	<2000	Category I

BioClean-D™ CleanTough White Material - ASTM F739-12 Test Method Results

Mean Breakthrough Time (MBT), Minutes

Breakthrough of the test chemical is deemed to have occurred when the permeation rate has reached 0.1 µg/cm²/min

CISPLATIN	CARMUSTINE	CYCLO- PHOSPHA- MIDE	DOXO- RUBICIN HYDRO- CHLORIDE	5- FLURO- URACIL	METHO- TREXATE	ETOPOSIDE	PACLITAXEL	THIOTEPA
>240	<6	217 (275,162,215)	>240	>240	>240	>240	<10	30 (28,30,33)

Results achieved under controlled laboratory conditions, by accredited external testing laboratory.

TO ORDER

Re-Order	Chest	Height	Size
BDFC-S	84-92cm (33"-36")	164-170cm (5'4"-5'6")	S
BDFC-M	92-100cm (36"-39")	170-176cm (5'6"-5'9")	M
BDFC-L	100-108cm (39"-42")	176-182cm (5'9"-6'0")	L
BDFC-XL	108-116cm (42"-45")	182-188cm (6'0"-6'2")	XL
BDFC-XXL	116-124cm (45"-48")	188-194cm (6'2"-6'4")	XXL
BDFC-XXXL	124-132cm (48"-51")	194-200cm (6'4"-6'6")	XXXL
BDFC-XXXXL	132-140cm (51"-54")	200-206cm (6'6"-6'8")	XXXXL

Packing

One piece per sealed inner PE bag; one inner bag per sealed outer PE bag; 20 outer bags per lined carton (20 pieces).

Please note: sizes XXXL & XXXXL 15 pieces per carton.

All sizes subject to minimum order quantity and lead time.

*NOTE: BioClean CleanTough material is static dissipative and, with a charge half decay time of 0.07 sec, BDFC is ideal for use in a static-safe environment. However BDFC should not be relied upon to earth the wearer.

For additional information visit us at www.bioclean.com, or call us at +44 1638 663338

Nitritex Ltd

Minton Enterprise Park,
Oaks Drive
Newmarket, Suffolk, CB8 7YY
United Kingdom
Tel: +44 1638 663338

Ansell US

111 Wood Avenue South
Suite 210
Iselin, NJ 08830
USA
Tel: +1 800 800 0444

Nitritex (M) Sdn Bhd

No.2, Jalan Jurunilai U1/20, Seksyen U1
Hicom Glenmarie Industrial Park
40150 Shah Alam, Selangor
Malaysia
Tel: +603 5569 3857/3859



BDFC/1906/PDS23

Neither this document nor any other statement made herein by or on behalf of Ansell should be construed as a warranty of merchantability or that any Ansell product is fit for a particular purpose. Ansell assumes no responsibility for the suitability or adequacy of an end user's selection of disposable garments for a specific application.

**Please see product validation pack or contact Ansell customer service for specific data on use of garments with cytotoxic drugs. Garments used for protection against such drugs must be selected specifically for the type of chemicals used.

Ansell, ® and ™ are trademarks owned by Ansell Limited or one of its affiliates. © 2012 – 2019 Ansell Limited. All Rights Reserved.