

## **About**

Offering comfort, flexibility and elbow length protection, the 400mm (16") BioClean Legion Latex Glove is the natural choice. With a textured surface for enhanced grip, the ambidextrous natural-colour glove is powder-free and double-donnable.

# Specifications

COMPATIBILITY:

ISO Class 5

LENGTH:

400mm (16")

MATERIAL:

Latex

PROTEIN LEVEL:

Less than 50µg/gram

SURFACE:

**Textured** 

SHAPE:

**Ambidextrous** 

COLOUR:

Natural

#### **Features**

- Flexible and comfortable
- Elbow length for extra protection
- Powder-free
- Easy double-donning
- Non-particulating EasyTear packaging









# **BIOCLEAN LEGION**

Non-sterile Latex Gloves RI A3

**ELBOW LENGTH PROTECTION** 

FLEXIBLE & COMFORTABLE

DOUBLE-DONNABLE



Ms.G.Love© represents BioClean's range of cleanroom gloves



# Quality Standards

- Manufactured in a facility holding ISO 9001: 2008 and 89/686/EEC Article 11b certifications
- Conforms to Category 3 Complex Design Personal Protective Equipment PPE Directive 89/686/EEC
- Processed in an NEBB certified ISO Class 5 environment
- Complies with the requirements of Glove Standard EN420:2003 and EN374-1, 2 & 3:2003
- Physical properties comply with European Medical Glove Standard EN455-2:2009
- Suitable for contact with dry, alcoholic and acidic foodstuffs.

# Shelf Life & Storage

Five (5) years from date of manufacture. Store in a dry, cool place (<40°C) away from direct sunlight and fluorescent light.

# **Physical Properties**

CHARACTERISTICS	VALUE	TEST METHOD	
Freedom From Holes	1.5 AQL Performance Level 2	EN 374-2:2003	
	1 Griormaneo 26ver 2		
Glove Length	400/16	EN 420:2003	
+/-10mm (mm/inches)			
Single Wall Thickness	Cuff: 4.33/0.11	EN 455-2:2009	
Minimum (mils/mm)	Palm: 6.69/0.17		
	Finger Tip: 7.87/0.20		
Force At Break During Shelf Life	≥ 9 N	EN 455-2:2009	

PALM WIDTHS (mm) ± 5mm							
SIZE	Small	nall Medium Lar		XLarge			
mm	83	95	106	115			
TEST METHOD			EN 420:2003				

# Glove Cleanliness Characteristics

PARTICLES			TYPICAL PARTICLE COUNT		TEST METHOD			
$\geq 0.5 \mu m (counts/cm^2)$			<2250		IEST-RP-CC005.4			
TYPICAL EXTRACTABLE IONS						TEST METHOD		
ANIONS	Fluoride	Chloride	Nitrite	Bromide	Nitrate	Phosphate	Sulphate	IEST-RP-CC005.4
(µg/cm²)	0.005	1.968	ND	ND	0.277	ND	0.538	
CATIONS	Lithium	Sodium	Ammonium	Potassium	Calcium	Magnesium	Zinc	
(µg/cm <sup>2</sup> )	ND	0.022	0.055	0.095	0.813	0.020	ND	
ND = Not Detected, NT = Not Tested, NA = Not Applicable								





# TO ORDER

Re-order code

BLA301-S

BLA302-M

BLA303-L

BLA304-XL

Size

Medium

Medium

XLarge

XLarge

### **Packing**

100 pieces per sealed inner PE bag; one inner PE bag per sealed outer PE bag; 10 outer bags per lined carton (1000 pieces)

#### For additional information visit us at www.bioclean.com, or call us at +44 1638 663338

#### Nitritex Ltd Minton Enterprise Park Oaks Drive Newmarket, Suffolk CB8 7YY United Kingdom

BLA3/1806/PDS35



Caution: This product contains natural rubber latex (latex) which may cause allergic reactions in some users. Safe use of this glove by or on latex sensitized individuals has not been established.

Neither this document nor any other statement made herein by or on behalf of Ansell should be construed as a warranty of merchantability or that any Ansell product is fit for a particular purpose. Ansell assumes no responsibility for the suitability or adequacy of an end user's selection of gloves for a specific application.

\*Warning: No glove provides complete protection against all chemicals. Users must test the gloves against the particular chemicals and environment in which they will be used.

\*\*Please see product validation pack or contact Ansell customer service for specific data on use of gloves with cytotoxic drugs. Gloves used for protection against such drugs must be selected specifically for the type of chemicals used.

Ansell, ® and TM are trademarks owned by Ansell Limited or one of its affiliates. © 2012 - 2018 Ansell Limited. All Rights Reserved.